

Soarnol™ D2908HB

ETHYLENE VINYL ALCOHOL COPOLYMER

Modified Soarnol™ for the hot-water under floor heating pipe

Application

Soarnol™ D2908HB is a special grade of Soarnol™, its ethylene content is 29 mol% with an intermediate MFR (melt flow rate).

Soarnol™ D2908HB has a better thermal durability, therefore it can be used as the oxygen barrier component of the under floor heating pipe.

General Properties

Properties	Unit	Value
Ethylene Content	mol%	29
MFR ¹⁾ (210 degree C, 2160g)	g/10min	8.0
Volatile Matter	%	≤0.30
Melting Point ²⁾	degree C	188
Crystallization Temp. ²⁾	degree C	163
Glass Transition Temp. ²⁾	degree C	62
Density ³⁾ (23 degree C)	g/cm ³	1.21
Oxygen Permeability ⁴⁾ (20 degree C x 65%RH)	cc.20μm / m ² .day.atm cc.mil / 100inch ² .day.atm	0.1 0.005

1): Measured with Melt Indexer

2): Measured with DSC, both heating and cooling speeds of 10 degree C/min

3): Measured with Micromeritics Gas Pycnometer

4): Measured with OXTRAN 2/22 (MOCON)

*The above figures are representative values and are not guaranteed.

Melt Viscosity




Fig. 1 Melt Viscosity of Soarnol™ D2908HB

Example of Processing

Extruder : 40 mmφ L/D = 28
 Screw : full flight, constant pitch type, C.R. = 3.5
 Screen pack : 90/90 mesh

Processing Temperature (degree C)

C ₁	C ₂	C ₃	C ₄	C ₅	AD
190-210	200-220	210-230	210-230	210-230	210-230

Thermal Durability




Fig. 2 Thermal Durability of Soarnol D2908HB

Quality and Safety for Application of Soarnol™ D2908HB

High quality Soarnol™ is produced by Okayama plant in Japan, Mitsubishi Chemical America Inc. in U.S.A. and Mitsubishi Chemical UK Ltd. in U.K.. All plants are certified to meet the requirement of ISO 9001.

Soarnol™ contains no heavy metals or other harmful substances.

MITSUBISHI CHEMICAL CORPORATION

Soarnol Dept. Polymers Division, Polymers & Compounds / MMA Business Group

Mitsubishi Chemical Corporation Head Quarters	1-1, Marunouchi 1-Chome, Chiyoda-Ku, Tokyo 100-8251, Japan TEL +81-3-6748-7803
Soarus L.L.C	3930 Ventura Drive, Suite 300, Arlington Heights, IL 60004, USA TEL +1-847-255-1211
Mitsubishi Chemical Europe GmbH	Schiesstraße 47, 40549 Düsseldorf, Germany TEL +49-211-52054-10
Mitsubishi Chemical (China) Co.,Ltd.	38-39th Floor, Grand Gateway Office Tower 1, 1 Hongqiao Rd.,Xuhui District, Shanghai, 200030 China TEL +86-21-5407-6161
Mitsubishi Chemical Singapore Pte. Ltd.	41 Science park Road #02-12/13 The Gemini Singapore Science Park II Singapore 117610 TEL +65-6279-0200
Soarnol Laboratory	3-10, Ushiodori, Kurashiki, Okayama 712-8054, Japan TEL +81-86-455-5214

URL: <http://www.soarnol.com/>
<https://www.m-chemical.co.jp/>