



Soarnol®


ETHYLENE-VINYLAALCOHOL COPOLYMER



H4815B

48 mol% Ethylene Content





[General Description]

Soarnol H4815B is one of the standard grades of “Soarnol®”, its ethylene content is 48 mol% with a high MFR(melt flow rate).

Soarnol H4815B has the best water resistance of all Soarnol grades and good gas barrier property, especially in high humidity environments. Its gas barrier property is not drastically lower at high humidity. This resin is used in coextruded film, coextrusion coating and shrink packaging.

[General Properties]


<i>Property</i>	<i>Unit</i>	<i>Value</i>
Ethylene Content	mol%	48
MFR ¹⁾ (@210deg C, 2160g)	g/10min	15
Volatile Matter	%	< 0.3
Melting Point ²⁾	deg C	158
Crystallization Temperature ²⁾	deg C	138
Oxygen Permeability ³⁾	cc 20 μ m / m ² day atm	4.8
20deg C-75%RH	cc·mil/100inch ² ·day·atm	0.244
WVTR	g 30 μ m / m ² 24hrs	12-25
40deg C-90%RH		

1): Measured with Melt Indexer

2): Measured with DSC, both heating and cooling speeds of 10deg C /min

3): Measured with OXTRAN 10/50 (MOCON)





[Melt Viscosity]




Fig.1 Melt Viscosity of Soarnol H4815B


[Example of Processing]

- Extruder: 40 mm ϕ single screw extruder, L/D = 28
- Screw: Full-flighted, constant pitch type, CR = 3.5
- Screen pack: 80/120/50 mesh
- Die: Manifold type, die width = 450 mm, lip clearance = 0.2 mm

Processing Temperature: deg C(deg F)

C ₁	C ₂	C ₃	C ₄	C ₅	Head	Die
170	190	210	220	220	220	190-220
(338)	(374)	(410)	(428)	(428)	(428)	(374-428)





[Hygienic Performance of Soarnol H4815B]

Soarnol H4815B contains no heavy metals or other harmful substances.
Soarnol H4815B meets the Food Sanitation Standards of various countries.

Japan: Ministry of Health and Welfare Announcement No.370(Dec. 28,1959)
and Its Latest Amendment No.18(Jan. 31,1994)

Self-Restrictive Requirements on Food-Contacting Articles
Made of Polyolefins and Certain Polymers

U.S.A.: FDA 21CFR 177.1360(a)(3) and 175.105

E U: European Commission Directive 90/128/EEC,
and Its Latest Amendment

Date Revised: April. 4, 2008

The Nippon Synthetic Chemical Industry Co., Ltd

Head Office	:	Umeda Sky Building, 1-88, Oyodonaka 1-chome, Kita-ku, Osaka 531-0076, Japan	TEL 81-6-6440-5313	FAX 81-6-6440-5326
Tokyo Office	:	Mitsui Sumitomo Insurance TEPCO Bldg., 6-1, Kyobashi 1-chome, Chuo-ku, Tokyo 104-0031, Japan	TEL 81-3-3564-7009	FAX 81-3-3564-7015
Nagoya Office	:	Dainagoya Building, 28-12, Meieki 3-chome, Nakamura-ku, Nagoya 450-0002, Japan	TEL 81-52-565-3538	FAX 81-52-565-3574
Central Research Laboratory	:	13-1, Muroyama 2-chome, Ibaraki, Osaka 567-0052, Japan	TEL 81-726-43-2256	FAX 81-726-43-2257
Kyushu Office	:	Daihaku Center Building, 19-24, Hakata-Ekimae 2-chome, Hakata-ku, Fukuoka 812-0011, Japan	TEL 81-92-432-0104	FAX 81-92-432-0122
Processing-Technique Development Center	:	8-1, Matsue 4-chome, Kurashiki, Okayama 712-8052, Japan	TEL 81-86-455-5214	FAX 81-86-455-5289
NIPPON GOHSEI Europe GmbH	:	Merowingerplatz 1a, D-40225, Düsseldorf, Germany Life Science Center	TEL 49-211-385488-0	FAX 49-211-385488-29
NIPPON GOHSEI UK Ltd.	:	Unit 14 Marina Court, Castle Street, Hull HU1 1TJ, UK	TEL 44-1482-333320	FAX 44-1482-333325
NOLTEX L.L.C.	:	12220 Strang Road, La Porte TX 77571-9740, USA	TEL 1-281-842-5000	FAX 1-281-842-5095
SOARUS L.L.C.	:	3930 Ventura Drive, Suite 440 Arlington Heights, IL 60004, USA	TEL 1-847-255-1211	FAX 1-847-255-4343
Shanghai Office	:	Room 4211A The Center, No.989 ChangLe Road, Shanghai Post Code 200031	TEL 86-21-5407-6333	FAX 86-21-5407-6038

URL: <http://www.soarnol.com/>
<http://www.nichigo.co.jp/>

