

< General Property of Soaresin PG505 >

Property	Unit	Value
MFR ¹⁾ (@190 , 2160g)	g/10min	5.3
Melting Point ²⁾	degC	113
Crystallization Temperature ²⁾	degC	101

1): Measured with Melt Indexer

2): Measured with DSC, both heating and cooling speeds of 10deg C /min