

< General Property of Soarnol TF2905B >

Property	Unit	Value
Ethylene Content	mol%	29
MFR <sup>1)</sup> (@210 , 2160g)	g/10min	5
Volatile Matter	%	< 0.3
Melting Point <sup>2)</sup>	degC	188
Crystallization Temperature <sup>2)</sup>	degC	163
Oxygen Permeability <sup>3)</sup> 20deg C-65%RH	cc 20 μ m / m <sup>2</sup> day atm	0.5

1): Measured with Melt Indexcer

2): Measured with DSC, both heating and cooling speeds of 10deg C /min

3): Measured with OXTRAN 10/50 (MOCON)