

Organic Solvent Barrier Property of “Soarnol™”

Organic solvent barrier property of “Soarnol™” is shown in the following.

Sample	Thickness (μm)	Permeability ($\text{mg}/\text{cm}^2 \cdot \text{day}$) at 20deg C	
		Chloroform	Kerosene
Soarnol 32mol%	20	0.20	<0.005
Soarnol 44mol%	20	0.31	<0.005
ONy	25	1.35	0.03
PET	25	31.0	0.05
KON	15	0.87	<0.005